



ZELPA HANDELSGES.M.B.H.

SPECIFICATION FOR SEMIBLEACHED SOFTWOOD SULPHITE PULP

Tensile strength	8,100 – 8,400 m
Broken; quantity of double bend	400
Brightness, %	63 - 64
Resin content, %	1.2 - 1.4
pH water extract of pulp	6,0 – 7,0
Dirt-count:	
0,1-1,0 mm ²	650 - 750
1,0-2,0 mm ² (max)	20
2,0 mm ² (max)	3
Moisture content, % (max)	20,0

Packing-bales (175 kg), sizes 660x800x550 mm tied up with wire.

Zelma HandelsGmbH

www.zelma.at

Domicile: Donizettiweg 27, A-1220 Vienna, Austria ▲ Commercial Register No. FN 128407 I ▲ Commercial Court Vienna
EURO Bank Account No. 310039-00626 at Erste Bank der Oesterreichischen Sparkassen AG, Vienna
IBAN: AT 98 20111 310039 00626, BIC: GIBAATWWXXX