



ZELPA HANDELSGES.M.B.H.

PRODUCT DATA SHEET FOR
Bleached Sulfate Softwood Pulp
Grade HD-Extra, HB-1*

Parameter		HB-Extra	HB-1*	Method
Beating characteristics at 60 SR				
Breaking length, km	not less than	9.0	8.5	GOST 13525.1
Tear Index, mH*m2/g	not less than	9.0	8.3	GOST 13525.3
Brightness, %	not less than	89	89	GOST 30437
Dirt count	not more than	5	15	GOST 14363.3
pH		5.5 – 7.0	5.5-7.0	GOST 12523 and i.3 GOST 9571
Moisture content, %	not more than	20	20	GOST 16932 pr. 3

Zelpa HandelsGmbH

www.zelpa.at

Contact Details: Tel.: +43-1-9205588, Mobile: +43-664-9184488, E-Mail: office@zelpa.at, Web: www.zelpa.at
Domicile: Donizettiweg 27, A-1220 Vienna, Austria ▲ Commercial Register No. FN 128407i ▲ Commercial Court Vienna
USD Bank Account No. 281423- 06606 at Erste Bank der Oesterreichischen Sparkassen AG, Vienna
IBAN: AT51- 20111-281423- 06606, BIC: GIBAATWWXXX